



112009

INDUSTRIAL THREADED PRODUCTS INC.

13580 FIRESTONE BLVD. , SANTA FE SPRINGS, CA 90670

800-976-BOLT FX: 800 646 4249

www.itpbolt.com

NON-ASBESTOS GASKET

SUBMITTAL SPECIFICATIONS

GASKETS MEET THE PRESSURE RATINGS, DRILLING AND DIMENSIONS OF ANSI / ASME B16.21

TECHNICAL DATA

PRODUCT	STYLE	COLOR	BINDER	TEMP MAX	PRESSURE MAX	PRESS X TEMP MAX	COMPRESS. ASTM F-36	RECOVERY ASTM F-36	TENSILE STRENGTH ASTM F152	FLEXIBILITY	CREEP RELAXATION ASTM F-78
KLINGER	4401	GREEN	NBR	750°	1400 PSI	400,000	7-17	50%	2000	PASSED	20
TEADIT	NA 1001	GRN/WHT	NBR	750°	1370 PSI	350,000	11	60%	1740	-	27

AVAILABILITY

FULL FACE RING 1/16" 1/8" 1/4"

SERVICE: Suitable against Air, Water, Brine, Sludge, Low Pressure Steam, Organic and Weak In-Organic Acids, Concentrated and Diluted Alkalis (PH Range From 1 to 11), Chemicals, Petroleum and Petroleum Derivatives, Synthetic Oils, Animals Fats, Vegetable Oils, Aromatic and Aliphatic Solvents, Chlorinated Solvents and Refrigerants. These Gasket materials meet the pressure ratings, drilling and dimensional requirements of ANSI/ASME B16.21 and AWWA C207-94.

GENERAL DESCRIPTION: Manufactured from a Non-Asbestos Material formulated for services in most sealing applications as a universal replacement gasket. The synthetic fiber content is Aramid Bound by Nitrile Rubber (NBR) or Neoprene Rubber (CR). These gaskets have a non-stick coating.

**Neoprene is a registered trademark of Dupont.

12027 Arrow Route
Rancho Cucamonga, CA 90670
909-466-9445
fx: 909-945-2696

2145 South 11th Ave. Ste 130
Phoenix, AZ 85007-4199
800-976-2658
fx: 800-646-4249

174 Lawrence Drive Unit E
Livermore, CA 94550
800-566-8831
fx: 800-646-4249

1832 G Street
Fresno, CA 93706
559-233-2957
fx: 559-233-2961