

# NEOPRENE FACED PHENOLIC INSULATING KIT

## SUBMITTAL SPECIFICATIONS

### NEOPRENE FACED PHENOLIC GASKET 1/8 THICK

DIELECTRIC VOLTS/MIL ASTM D149	COMPRESSIVE STRENGTH (PSI) ASTM D695	WATER ABSORPTION ASTM D229	HARDNESS ROCKWELL "M" ASTM D785	TENSILE (PSI) ASTM D638	SHEAR (PSI) ASTM D732	OPERATING TEMP (MAX)
500	25,000	1.6	85	20,000	18,000	175

### MYLAR SLEEVE MATERIAL PROPERTIES

4000	N/A	2.0%	M=100	N/A	N/A	300
------	-----	------	-------	-----	-----	-----

### PHENOLIC 1/8" WASHER PROPERTIES

550	50,000	0.10	N/A	N/A	N/A	N/A
-----	--------	------	-----	-----	-----	-----

### BACK UP WASHERS

(2) STEEL PLATED     (2) F436 HARDENED STEEL     (2) 306 STAINLESS STEEL WASHERS

(2) 316 STAINLESS STEEL WASHERS

Materials for Flange Insulating Kits on pipes containing water and natural gas (up to 221 F, 105 C) shall consist of the following components.

**INSULATING GASKET:** Neoprene Faced Phenolic Gaskets have been used primarily in the water, oil, and gas industries for many years. Soft Neoprene rubber sheets are factory applied to both sides of a laminated phenolic retainer providing an effective sealing surface.

**FULL LENGTH INSULATING SLEEVES:** Made of 1/32" wall thickness Mylar tubing.

**WASHERS:** The I.D. of all washers shall fit over the insulating sleeve and both the steel and insulating washer shall have a same I.D. and O.D.