



\*Kanebridge Part Number

### Notes on Rivet Selection

*Strength-* The tensile and shear strengths required for an application must be determined and a rivet selected that meets those requirements.

*Materials-* Choose a rivet that is made of a metal with similar mechanical and physical properties as the materials being joined. This is especially critical in assemblies where higher temperatures and/or corrosive elements are present. Metal compatibility helps reduce the risks of galvanic corrosion and material fatigue.

*Grip Range-* Measure the total thickness of the materials being fastened. This is known as the "rivet grip". The grip ranges of the most commonly available rivets are listed in the table below. Sufficient rivet length is necessary for proper formation of the secondary head on the blind side of the assembly. Multi-grip rivets have wider grip ranges than standard blind rivets which are listed on pages 144-154.

### APPLICATION DATA FOR STANDARD BREAK-STEM BLIND RIVETS

SAE J-1200

Rivet Number	Grip Range	Barrel Length	Recommended Hole Size		Drill Size	Rivet Number	Grip Range	Barrel Length	Recommended Hole Size		Drill Size
			Max	Min					Max	Min	
31	.020-.062	.187	0.100	0.097	#41	516	.876-1.000	1.175	0.164	0.160	#20
32	.020-.125	.250				62	.020-.125	.325	0.196	0.192	#11
33	.087-.187	.312				64	.188-.250	.450			
34	.126-.250	.375				66	.251-.375	.575			
41	.020-.062	.212	68	.376-.500	.700						
42	.063-.125	.275	610	.510-.625	.825						
43	.126-.187	.337	612	.626-.750	.950						
44	.188-.250	.400	614	.751-.875	1.075						
45	.251-.312	.462	616	.876-1.000	1.200						
46	.313-.375	.525	618	1.001-1.125	1.325						
48	.376-.500	.650	620	1.126-1.250	1.450						
52	.020-.125	.300	0.164	0.160	#20	622	1.251-1.375	1.575	0.261	0.257	F
53	.125-.187	.362				84	.126-.250	.500			
54	.188-.250	.425				86	.251-.375	.625			
56	.251-.375	.550				88	.376-.500	.750			
58	.376-.500	.675				810	.501-.625	.875			
510	.501-.625	.800				812	.626-.750	.990			
512	.626-.750	.925				816	.751-1.000	1.240			